

TEST REPORT

REPORT NUMBER : TURT180088698
APPLICANT NAME : Gökhan Boya San. ve Tic. Ltd. Şti.
ADDRESS : Kazımpaşa Mah. Çanakkale Asfaltı No:20Menemen İzmir / TURKEY
TEL:0232 832 73 02FAX:0232 832 73 97
Attention : Tuğçe İnan (tugce.inan@gokhanboya.com)
SAMPLE DESCRIPTION : One sample of 279 SERİ-POLİÜRETAN SERTLEŞTİRİCİ / 279 SERIES -
POLYURETHANE HARDENER
DATE IN : 9 May ,2018 (13:48:00)
DATE OUT : 14 May ,2018

TEST	SAMPLE
Toxic Elements Analysis	1 P

P = MEETS BUYER' S REQUIREMENT / F = DOES NOT MEET BUYER' S REQUIREMENT / NR = NO REQUIREMENT / SC=STILL CONTINUES / X=NOT PERFORMED / NA = NOT APPLICABLE / LS = LACK OF SAMPLE / NC = NO COMMENT / I = INCONCLUSIVE / # = SEE RESULT / NF = NEEDS FURTHER TESTING / A = ABSENT / M = MARGINAL ACCEPT / SD = SEE DETAILS ENCLOSED / FS: FURTHER STEPS

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025 and TÜRKAK accreditation requirements. Unless otherwise is specified, all Pass or Fail results are given without uncertainty considered. When uncertainty is taken into account, the result may be borderline. Borderline results need to be re-tested to determine their disposition up to customer's decision. Opinions and interpretations expressed herein are outside the scope of TÜRKAK accreditation. Tests marked (*) in this test report are not included in the TÜRKAK accreditation schedule for this laboratory.



Volkan ALBAYRAK
Customer Care Executive



Zeynep AKIN
Chemical Laboratory Manager

Intertek Test Hizmetleri A.S.
Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna-34197 /ISTANBUL
Phone : +90 212 496 46 46 Fax: +90 212 452 80 55
e-mail : intertekcg.turkiye@intertek.com
<http://www.intertek-turkey.com>



180088698

Test Method	Results	Requirements
-------------	---------	--------------

Toxic Elements Analysis

BS EN 71-3 : 1995

Acid extraction method was used and toxic elements content were determined by Inductively Coupled Plasma ICP_OES.

	Result	Detection Limit	Requirement
Antimony (Sb)	Not Detected	2 ppm	60 ppm
Arsenic (As)	Not Detected	2 ppm	25 ppm
Barium (Ba)	Not Detected	2 ppm	1000 ppm
Cadmium (Cd)	Not Detected	2 ppm	75 ppm
Chromium (Cr)	Not Detected	5 ppm	60 ppm
Lead (Pb)	Not Detected	5 ppm	90 ppm
Mercury (Hg)	Not Detected	2 ppm	60 ppm
Selenium (Se)	Not Detected	2 ppm	500 ppm

ppm : part per million (mg/kg)
< =Less Than

Estimated Total Uncertainty=(Results quoted have been corrected for uncertainty.)

END OF TEST REPORT